MEMORIAL SPECIFICATION GUIDE



Materials
Finishes
Shapes
Lettering
Ornament

When producing a new memorial, consideration must be given to the customer's requirements, location and cemetery and churchyard regulations. A durable, naturally quarried material should be selected which will accommodate the required design and lettering.

Materials

All materials used in the production of memorials have variations within the slab. Colour names can be misleading and are only given as a general guide.

"GRANITES"

These are the hardest materials and cover all igneous stones. Colours range from black to light grey, pink to red, blue and green. Some have a pearl effect when polished showing the mica within the rock.

Finishes: All types

"MARBLE"

Carrara, sometimes called Sicilian is the usual marble used for memorials. Marble is generally white and has a blue grey vein. As it weathers it turns grey and becomes sugary, due to surface erosion.

Finishes: All types except polishing

"LIMESTONE"

The material is formed under water and contains shells, as in Portland stone. The colour ranges from cream to beige. Nabresina from Trieste in Italy is denser and finer grained than many British Stones.

Finishes: All types except polishing

"SANDSTONE"

Silica stones, such as York, can be harder and more durable than Limestone. The colours vary from sandy to grey.

Finishes: Fine rubbed, tooled or pitched.

"SLATE"

Chemically similar to clay, this material is compressed into laminated form and is very strong. It can be split or sawn into thin slabs. It is usually blue/black or green.

Finishes: Fine honed or Riven - split through the lamination

Finishes

RUSTIC

Natural rock-like appearance achieved with a minimum of work to split away unwanted stone.

PITCHED

Natural rock finish left by splitting the material by hand or machine.

PUNCHED

As rustic but highest spots reduced by tooling.

FINE PUNCHED

As punched but material is worked to give a reasonably uniform surface.

FINE AXED

A rustic finish finely tooled to give an even surface, used on rough granite for inscription panels.

FLAME TEXTURED

Surface is spalled or exfoliated by the application of heat, giving a uniform appearance similar to riven.

RIVEN

Naturally split giving a smooth undulating surface, only applies to slate.

TOOLED

Various textures achieved by masoning, normally a dressed finish showing tool marks.

Sparrow Peck

A tooled even texture achieved with a finely pointed chisel.

SANDED

Fine rubbed or sandblasted to remove the irregular markings, giving a uniform surface.

EGGSHELL

Non-reflective smooth matt finish.

HONED

Finish between eggshell and polished.

POLISHED

A gloss polished finish giving a glass-like smooth reflective surface.

Standard Headstone Shapes



Standard Headstone Shapes (continued) H32 Desk with Pilasters H31 Desk H33 Scroll with Side Panels H35 H36 H37 H38 Convex Face Split Headstone Split with Wings Concave Face H42 Upright Scroll H40 H39 H41 Serpentine Top Recumbent Scroll Heart With ogee shoulders Curved or Barrel Sides **Plaques and Tablets** P2 Scotia Desk Desk with Container Hole P8 Desk & Vase


Plain Plaque, Vase & Base

Plain Plaque, Riser & Base


Plain Plaque, Rest & Base


Lawn Type Bases

shown with typical dowel and container holes




Crosses





Die and Step Bases for Crosses




DS2 Three Tier Stepped Base


DS1
Die and Weathered Plinth **Books and Supports**




Open Book with Curved Pages




Open book with Curved Pages and Tassel




BK3 Open Book with Flat Pages




BK5 Tick Rest




Closures



Post with Kerbs



Square Return




Mitred Return

Kerb Ends




K1 Half Bullnose



Scotia



Splay



Check & Ogee

Kerb Sections



Square



K6 Deep Chamfer or Splay



Check or Rebate



Scotia



Chamfer



K10 Half Bullnose



Roll Top



Flat

Posts



Plain



P2 Check



Р3 Chamfer with Container Hole




Mitre




Peon

Kerb Surrounds Ledgers and Cover Slabs




Examples of Canopies






Obelisk




Vases


Vases should be in keeping with the general design of the rest of the memorial and, if possible, provide room for an inscription.




V1 Check Top




V2 Chamfer Top




V3 Plain




V8 Ovolo




V9 Check Sides



V10 Panelled



V5 Splay Sides




V6 Tapered Sides




V4 Round with Container


Mouldings & Shapes





Lettering




Incised Roman Capitals









Raised or Embossed









Incised Sans Serif or Block Characters







Square Incised


Grit Blasted


Flush Lead

The material is drilled at an angle to the face to give a key. Lead is beaten in and cleaned off smooth









Square Incised

Incised


Embossed


Sand Blasted


Cross Sections


Method 1

Rough out the letter shape as shown on plan and drill holes at different angles to form a key, then beat in the lead, filling the holes and rough cut letter, but leaving the lead a uniform, smooth thickness above the surface of the stone, trimming the lead to form the letter shape and enamelling, usually black.















Method 2


Drill the holes directly into the surface of the stone at different angles, then beat in the lead repeating the same procedure as Method 1.

Raised Lead Letters

There are two methods of creating raised lead letters as shown above.

Ornamentation








Sunk Relief

Outline



Skin Carved on White Marble





Etched and Shaded



Published by:

National Association of Memorial Masons 27a Albert Street

Rugby

WARWICKSHIRE CV21 2SG

Tel: 01788 542264 ♦ Fax: 01788 542276 e.mail: enquiries@namm.org.uk ♦ Web site: www.namm.org.uk

© COPYRIGHT NAMM

No reproduction by any method whatsoever of any part of this publication is permitted without the prior written consent of the copyright owners.

The National Association of Memorial Masons is indebted to

R. Lidster Ltd



the major sponsor of this publication.

Also to supporting sponsor

A & J Robertson (Granite) Ltd.

recenterate de control de control